

# LA-UR-17-21729

Approved for public release; distribution is unlimited.

Title: Phase diagram of URu2-xFexSi2 in high magnetic fields

Author(s): Ran, S.

Jeon, I.

Kanchanavatee, N.

Huang, K. Maple, M. B. Gallagher, A. Chen, K. Graf, D.

Baumbach, R. E. Singleton, John

Intended for: NHMFL 2016 Annual Research Report

Report

Issued: 2017-03-01





## NATIONAL HIGH MAGNETIC FIELD LABORATORY 2016 ANNUAL RESEARCH REPORT

## Phase diagram of URu2-xFexSi2 in high magnetic fields

Ran, S., Jeon, I., Kanchanavatee, N., Huang, K. and Maple, M. B. (UCSD, Physics); Gallagher, A., Chen, K., Graf, D., and Baumbach, R. E. (FSU, Physics); Singleton, J. (LANL, NHMFL)

#### Introduction

The search for the order parameter of the hidden order (HO) phase in  $URu_2Si_2$  has attracted an enormous amount of attention for the past three decades [1]. Measurements in high magnetic fields H up to 45~T reveal that  $URu_2Si_2$  displays behavior that is consistent with quantum criticality at a field near 35~T, where a cascade of novel quantum phases was found at and around the quantum critical point, suggesting the existence of competing order parameters [2]. Experiments at high pressure P reveal that a first order transition from the HO phase to a large moment antiferromagnetic (LMAFM) phase occurs under pressure at a critical pressure  $P_c$ [3].

We have recently demonstrated that tuning URu<sub>2</sub>Si<sub>2</sub> by substitution of Fe for Ru offers an opportunity to study the HO and LMAFM phases at atmospheric pressure [4]. In this study, we conducted electrical resistance measurements on URu<sub>2-x</sub>Fe<sub>x</sub>Si<sub>2</sub> for H < 65 T using the pulsed field facility at the NHMFL in Los Alamos, in order to establish the temperature T vs. H phase diagram of URu<sub>2-x</sub>Fe<sub>x</sub>Si<sub>2</sub> under magnetic fields.

#### **Results and Discussion**

For low Fe concentrations, after the HO phase is suppressed; another feature is found that is likely associated with the crossover from non-Fermi-liquid to Fermi-liquid behavior, as seen for the parent compound. For high Fe concentrations, the HO phase seems to reenter after the suppression of AFM, and is also suppressed completely. Representative phase diagrams are shown in Fig. 1.




Fig. 1. Temperature T vs. magnetic field H phase diagrams for  $URu_{2-x}Fe_xSi_2$  with x = 0.05 and 0.2.

#### **Conclusions**

We performed electrical transport measurements in high magnetic field on URu<sub>2-x</sub>Fe<sub>x</sub>Si<sub>2</sub> single crystals and established phase diagrams for the Fe substitution range of interest. In order to complete the phase diagram, we applied for 45 T hybrid field time and results are reported separately.

### **Acknowledgements**

Research at UCSD was supported by the US DOE BES under Grant No. DE-FG02-04-ER46105 (materials synthesis and characterization), the US NSF under Grant No. DMR-1206553 (low temperature measurements), and the NNSA under the SSAA Program through the US DOE under Grant No. DE-NA0002909 (high field measurements). Research performed at the National High Magnetic Field Laboratory (NHMFL) was supported by NSF Cooperative Agreement No. DMR-1157490, the State of Florida and the DOE.

#### References

- [1] J. A. Mydosh and P. M. Oppeneer, Rev. Mod. Phys. 82, 1301 (2011).
- [2] K. H. Kim, N. Harrison, M. Jaime, G. S. Boebinger, and J. A. Mydosh, *Phys. Rev. Lett.* 91, 256401 (2003).
- [3] N. P. Butch, J. R. Jeffries, S. Chi, J.B. Leão, J. W. Lynn, and M. B. Maple, *Phys. Rev. B* 82, 060408(R) (2010).
- [4] N. Kanchanavatee, M. Janoschek, R. E. Baumbach, J. J. Hamlin, D. A. Zocco, K. Huang, and M. B. Maple, *Phys. Rev. B* **84**, 245122 (2011).